

K-FLEX® SOLAR HT



K-FLEX® SOLAR HT

- ▶ ELASTOMERIC INSULATION FOR HIGH TEMPERATURES
- ▶ IDEAL SOLUTION FOR INDUSTRIAL AND SOLAR SYSTEMS
- ▶ INCREASED ENERGY EFFICIENCY
- ▶ EPDM WITH UV PROTECTION
- ▶ ALSO AVAILABLE WITH PROTECTIVE COATINGS FOR ADVERSE WEATHER CONDITIONS

> Site <



> App. Manual <





Property	Value	Test method
Temperature range	From -40 °C to +150 °C	EN 14706 EN 14707
Thermal conductivity λ W/(m•K)	0 °C = 0,040 40 °C = 0,044	EN 13787 EN 12667 EN ISO 8497
Corrosion prevention	pH neutral (7±0,5)	EN 13468
Fire rating	Euroclass E	EN 13501-1

K-FLEX® reserves the right to change data and technical requirements without notice.

INFO ▶ K-FLEX® SOLAR HT

Elastomeric EPDM (Ethylene-Propylene Diene Monomer) rubber based insulation with excellent mechanical properties suitable for high temperatures. Good UV resistance.

The rational and convenient solution for solar panels and industrial processes up to 150 °C. A new, revolutionary box, tailor-made for the client, offering practical and economical advantages for use and distribution.



High temperature insulation

RANGE ▶ K-FLEX® SOLAR HT

	LENGTH	THICKNESSES	DIAMETERS
K-FLEX® SOLAR HT - Tubes	2 m	13-19-25 mm	from 10 to 89 mm
K-FLEX® SOLAR HT - Rolls		13-19 mm	15-18-22 mm

	THICKNESSES	HEIGHT
K-FLEX® SOLAR HT - Sheets	10-13-19-25-32 mm	1000 mm



PROJECTS ▶
K-FLEX® SOLAR HT

Zamo, Poland
Hospital

